

# 4032 Double Coated Foam Tape

# **Product Data Sheet**

Updated : February 1996 Supersedes : November 1993

### **Product Description**

A-20 is a firm acrylic pressure sensitive adhesive system. It features high ultimate bond strength, high temperature and solvent resistance and very

high shear holding power. Bond strength increases substantially with time.

## **Physical Properties**

Not for specification purposes

Adhasiya Typa	Acrylic	<b>3M ref</b> : A-20
Adhesive Type	Actylic	SWITEL . A-20
Foam Core	Polyurethane Foam (Open Cell)	Foam Density 320 kg/m³
Thickness (ASTM D-3652)		
Tape Liner Total	0.80 mm 0.08 mm 0.88 mm	
Thickness Tolerance	0.64 - 1.02 mm	
Release Liner	Green Plaid Paper	
Tape Colour	Natural	
Shelf Life	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

### Performance Characteristics

Not for specification purposes

Static Shear Strength weight held for 100 hours to stainless steel with ½ sq in (3.23 sq cm) overlap	2000 g @ 20°C 1500 g @ 50°C 1000 g @ 65°C 1000 g @ 90°C	
Temperature		
Performance Max (hours/minutes) Max Continuous	190°C	
(days/weeks)	105°C	
Normal Tensile (T- Block)	41.5 N/cm <sup>2</sup>	
to Aluminium at room temp, 6.45 sq cm, jaw speed 50 mm/min.		
Solvent Resistance	No apparent degradation when exposed to splash testing of most hydrocarbon solvents.	
UV Light Resistance	No apparent degradation when exposed to 7 days in U. V. Chamber.	

Date: February 1996 4032 Double Coated Foam

Tape

# Additional Product Information

Cold Flex at -30°C(-20°F) No cracking when flexed

around a 6.4mm mandrel.

Thermal Conductivity (Watt/m Kelvin) 0.062 Dielectric Strength (Volts/25µm) 200-300

#### **Application Techniques**

- 1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength.
- 2. To obtain optimum adhesion, the bonding

surfaces must be clean dry and well unified. A typical surface cleaning solvent is isopropyl alcohol. Use proper safety precautions for handling solvents.

3. Ideal tape application temperature range is 21°C to 38°C (70°F to 100°F).

Initial tape application to surfaces at temperatures below 10°C (50°F) is not recommended because the adhesive becomes too firm to adhere readily. However once properly applied low temperature holding is generally satisfactory.

#### **Applications**

4032 urethane foam is soft, conformable and high in internal strength which makes it ideal for general purpose joining.

The excellent cold temperature properties of this product makes it suited for applications on snowmobiles, freezers etc.

3M and Scotch-Mount are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



**Specialty Tapes & Adhesives** 

Customer Service :

Tel 0161 236 8500 Fax 0161 237 1105 3M Ireland 3M House, Adelphi Centre, Upper Georges Street, Dun Laoghaire,Co. Dublin, Ireland © 3M United Kingdom PLC 1996

Tel (01) 280 3555 Fax (01) 280 3509

Customer Service:

3M United Kingdom PLC 3M House, 28 Great Jackson Street, Manchester, M15 4PA