

PROTEC

192.05.AA

Issued on 08-09-2006

Properties	Test procedures	Unit of measure	Values and Characteristics
Environmental condit. Temperature Atmospheric pressure Relative humidity		Celsius degree mmHg %	20° +/- 10% 760 +/- 5% 80 +/- 10%
Backing material			Polyolefins
Type of adhesive			Acrylic
Total thickness	AFERA 4006	mm.	0,055 +/- 7%
Backing tensile strength	ASTM D638	long. N/mm2. trasv.	>27 >17
Backing elongation at break	ASTM D638	long. % trasv.	>360 >570
Adhesion to steel	AFERA 4001	g/25 mm.	510 +/- 15%
Shelf life Storage	Internal method	month	6 at room temp.

Please note: environmental conditions do affect the adhesion level; some variations can be found even at slightly different temperatures (+/- 1 ° C.) from the stated ones. These variations do not change the general features of the product.

